

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61F 2/00, 2/28, A61K 33/42, C08G 81/00, 85/00, C08J 3/28, C08K 3/32	A1	(11) International Publication Number: WO 98/47445 (43) International Publication Date: 29 October 1998 (29.10.98)
(21) International Application Number: PCT/US98/07569 (22) International Filing Date: 16 April 1998 (16.04.98) (30) Priority Data: 08/844,378 18 April 1997 (18.04.97) US (71) Applicant: CAMBRIDGE SCIENTIFIC, INC. [US/US]; 195 Common Street, Belmont, MA 02178-2909 (US). (72) Inventors: WISE, Donald, L.; 195 Common Street, Belmont, MA 02178 (US). GRESSER, Joseph, D.; 40 Salisbury Road, Brookline, MA 02146 (US). TRANTOLO, Debra, J.; 28 Radford Road, Princeton, MA 01541 (US). HSU, Y., Y.; Apartment 204, 251 Buckminster Drive, Norwood, MA 02062 (US). (74) Agents: SCHURGIN, Stanley, M. et al.; Weingarten, Schurgin, Gagnebin & Hayes LLP, Ten Post Office Square, Boston, MA 02109 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: BIOERODIBLE POLYMERIC SEMI-INTERPENETRATING NETWORK ALLOYS FOR SURGICAL PLATES AND BONE CEMENTS, AND METHOD FOR MAKING SAME (57) Abstract A bioerodible polymeric semi-IPN alloy which comprises a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation; a second bioerodible polymer, which provides a biopolymeric scaffolding or internal reinforcement; and optionally a buffering compound that buffers the acidic products within a desired pH range. In a preferred embodiment, the second bioerodible polymer comprises polypropylene fumarate (PPF), which is cross-linked, desirably by a vinyl monomer such as vinyl pyrrolidone (VP) to form the biopolymeric scaffolding which provides the semi-IPN with dimensional and geometric stability.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**BIOERODIBLE POLYMERIC SEMI-INTERPENETRATING NETWORK ALLOYS
FOR SURGICAL PLATES AND BONE CEMENTS, AND METHOD FOR
MAKING SAME**

5

FIELD OF THE INVENTION

10

The invention relates to implantible biomaterials, in particular to bioerodible polymers and more specifically to bioerodible polymers suitable for use in forming internal fixation devices (IFDs) such as bone supports, plates, and pins, and/or bone cements for bone repair.

BACKGROUND OF THE INVENTION

15

20

25

A study in the mid-1980's estimated that about four and a half million people suffer fractures each year in the United States alone. In adults, fractures of the radius and/or ulna of the forearm, and fibula or ankle bone are frequently treated by immobilizing the fracture by the surgical attachment of a metal plate adjacent the fracture. Similarly, in some adults and most children, fractures of the neck of the femur or hip are frequently treated by immobilizing the fracture with a metal plate. In addition to its use in treating fractures of the radius, ulna and femur, a metal plate may also be used to immobilize other bones in both the treatment of fractures and in corrective surgery. The metal plate, typically made of a titanium-based metal, a stainless-steel, or a cobalt-chromium metal, is attached to the bone by bone screws. It should be noted that although the immobilization device is referred to as a plate, its size and shape is dictated by the application in which it is to be used.

30

35

As the bone heals it is necessary to remove the metal plate by means of a second surgical intervention. The reason for this is that the presence of the metal plate adjacent the bone ultimately results in what is referred to as "plate induced osteopenia" or loss of bone mass. The reasons for this loss of bone mass are not fully understood but appear

- 2 -

to be related both to changes in bone stress and changes in bone blood flow. Such bone remodeling in children may lead to growth restriction, especially when plates are used in craniofacial or maxillofacial intervention to repair congenital deformities.

Thus it is desirable to replace metallic surgical plates presently used in surgical procedures with a bioerodible polymer, i.e., one that will dissolve and be absorbed by the body as the underlying bone heals. With such a bioerodible plate, the necessity of a second surgical operation and its concomitant trauma is removed and the deleterious effects caused by the presence of a plate for a long period of time. Furthermore, unlike metals, these devices do not corrode and the modulus of the material may be more closely matched to that of bone. Two polymers that have been used to form bioerodible surgical plates are polylactic acid (PLA) and copolymers of lactic and glycolic acids (PLGA).

The mechanism for bioeroding polymers of lactic acid and copolymers of lactic and glycolic acids is not completely understood. The polymers are probably hydrolyzed *in situ* to their respective monomers and the resulting monomers are excreted from the body in the urine or expired from the body as carbon dioxide without ill effect. The body's tolerance of these monomers probably results from the fact that lactic acid and glycolic acid are present as natural substances within tissue.

Although polymers of, e.g., PLA degrade as desired, plates constructed of PLA have a tendency to "bow" in bone applications and thereby fail to appropriately immobilize fractures with respect to bending movements. This bowing apparently occurs because the side of the plate immediately adjacent the bone is exposed to a different aqueous environment than the side of the plate adjacent soft tissue. As water is adsorbed into the polymer, the polymer swells. Thus the difference in the aqueous environment of the two

- 3 -

surfaces of the plate causes a differential in the amount of water entering the plate through each surface. This differential water adsorption results in turn in the differential swelling of the two sides of the plate, with bowing therefore occurring. Thus it is desirable to form a surgical plate from a bioerodible polymer which is dimensionally and geometrically stable.

A related matter of interest in bone repair involves ensuring that the fractured bone ends are properly stabilized when set, and maintaining this stabilization during healing. A bioerodible bone cement could be used to bridge the area of excised bone fragments and thus aid in healing. Secondly, a bioerodible bone cement could additionally be used in conjunction with bone repair proteins (BRPs) to actively promote bone growth, i.e., the bone cement functions as an osteoinductive material. Also, because the rate of infection following total joint replacement surgery may be as high as 11%, it would also be desirable to incorporate various antibiotics into the bone cement for slow release at the surgical site to minimize infection. Ideally, therefore, such a bone cement or "grout" should be moldable in the surgical setting, set to form a strong solid, stabilize at the implant site, and support and aid the bone healing process.

With the use of minimally invasive techniques, a bioresorbable and/or osteoconductive bone cement could be used by injecting the cement into the fracture site under fluoroscopic control. This technique would help prevent complications such as repeated displacement, instability and malunion. The use of the cement may also warrant conservative treatment in patients with relative indications for operative management. These patients include older patients in whom long leg casting will be difficult to be mobile in, irreducible fractures, or one which has slipped in a cast, obese legs which limit the capability of casts to

- 4 -

maintain reduction, and chronic alcohol abusers. In addition, patients with relative contraindications to operative treatment, such as vascular insufficiency, diabetes mellitus, soft tissue blisters, abrasions, contusions or burns, could be successfully managed in a conservative fashion thus eliminating peri- and postoperative risk factors. Finally, patients with severe osteoporosis may benefit from the use of this osteoconductive bone cement as an adjunct to conservative treatment. Aside from its use in the treatment of ankle and foot fractures, a bioresorbable and osteoconductive cement may be applicable for the treatment of undisplaced or minimally displaced lateral tibial plateau fractures that would normally warrant conservative treatment (depression < 1 cm and valgus instability < 10 degrees).

Other potential applications include use in spinal fusions, where autologous bone grafting is often necessary and allogeneic bone is used when autologous bone stocks are insufficient. In these cases, an osteoinductive bioresorbable bone cement could serve as a bone substitute.

Thus a need exists for polymeric bioerodible materials which may be used in making bone cements which desirably have a wide range of precure viscosities (to allow injection of the cement to a bone site) and which also desirably incorporate biologically active agents. Such bioerodible bone cements containing biologically active agents for release must be able to protect the agents from damage during curing, and provide buffering capacity to obviate possible inflammatory foreign body response generated by bioerosion of the cement. Lastly, such polymeric bioerodible materials may also be used to make IFDs having dimensional stability during the critical bone setting and healing period.

SUMMARY OF THE INVENTION

The disclosure relates to bioerodible polymeric semi-interpenetrating network ("semi-IPN") alloys which comprise

- 5 -

5 a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation; a second bioerodible polymer, which, preferably via crosslinking, provides a biopolymeric scaffolding or internal reinforcement; and optionally a buffering compound that buffers the acidic products within a desired pH range. In a preferred embodiment, the second bioerodible polymer comprises polypropylene fumarate (PPF) which is cross-linked, desirably by a vinyl monomer such as vinyl pyrrolidone (VP) to form the biopolymeric scaffolding which provides the semi-IPN with the requisite dimensional and geometric stability. A beneficial end use of this material is in the form of internal fixation devices (IFDs) such as bone supports, plates, and pins, and/or bone cements for bone repair which are formed from the semi-IPN alloy disclosed herein.

10 Another aspect of the invention comprises a bone cement containing a bioerodible polymeric semi-IPN alloy comprising a first bioerodible polymer (such as PLGA) capable of producing acidic products upon hydrolytic degradation; and a second bioerodible polymer (such as PPF), which provides a biopolymeric scaffolding or internal reinforcement, wherein the second bioerodible polymer is polymerized *in vivo* to provide a hardened, semi-IPN alloy bone cement. Both the bone cement and dimensionally and geometrically stable IFDs of the disclosure of the invention may advantageously also contain other agents such as bone repair proteins (BRPs) and antibiotics, to, e.g., actively promote bone growth and prevent infection while the bone cement or IFD is in place.

BRIEF DESCRIPTION OF THE DRAWINGS

30 The invention will be more fully understood by reference to the following Detailed Description Of The Invention in conjunction with the following Drawings, of which:

FIGs. 1a and 1b are scanning electron micrographs (at 6250x) of a bone cement alloy according to the disclosure

- 6 -

containing crosslinked PPF scaffolding and PLGA/calcium gluconate after one and two weeks exposure to water.

FIG 2 is a graph of distribution of vinyl pyrrolidone between crosslinked poly(propylene fumarate) and poly(vinyl pyrrolidone). Linear regression analysis: intercept = - 0.082; slope = 1.084; correlation coefficient = 0.9686. (Example 2.)

FIG 3 is a graph of weight fraction of vinyl pyrrolidone incorporated into crosslinked poly(propylene fumarate) as a function of PPF/VP weight ratio. (Example 2.)

DETAILED DESCRIPTION OF THE INVENTION

The bioerodible bone cements and internal fixation devices (IFD) made from the bioerodible polymeric semi-IPN alloy material disclosed herein may be advantageously used for surgical repair of orthopaedic and maxillofacial fractures. The bioerodible material is a polymeric semi-IPN alloy which comprises at least a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation; and a second bioerodible polymer, which upon crosslinking provides a biopolymeric scaffolding or internal reinforcement.

An semi-interpenetrating polymer network (semi-IPN) is defined herein as an internecine combination of two or more polymers, at least one of which is crosslinked (sometimes in the immediate presence of the other) to form a network ("scaffolding" in the present disclosure) in which the other polymer is enclosed, trapped or retained.

As used herein, the term "bioerodible" is defined as the susceptibility of a biomaterial to degradation over time, usually months. "Buffer" is defined as any material which limits changes in the pH in the implant or cement and its near environment only slightly upon exposure to acid or base. "Acidic product" is defined herein as any product that has a pH less than 7.

- 7 -

The semi-IPN alloy of the invention includes a first bioerodible polymer that undergoes hydrolysis to produce acidic products when exposed to an aqueous medium. Examples of such bioerodible polymers include poly(lactide-co-glycolide) ($H[-OCHR-CO-]_nOH$, where R is H or CH_3) ("PLGA"); polydioxanone, poly(ϵ -caprolactone); polyanhydrides; poly(ortho esters); copoly(ether-esters); polyamides; polylactones; polypropylene fumarates ($H[-O-CH(CH_3)-CH_2-O-CO-CH=CH-CO-]_nOH$); and combinations thereof. In a preferred embodiment, the polymer poly(lactide-co-glycolide) $H[-OCHR-CO]_nOH$, R=H, CH_3 (PLGA) is used. The PLGA polymers used according to the invention have a lactide to glycolide ratio in the range of 0:100% to 100:0%, inclusive, i.e., the PLGA polymer can consist of 100% lactide, 100% glycolide, or any combination of lactide and glycolide residues. These polymers have the property of degrading hydrolytically to form lactic and glycolic acids.

Selection of a suitable first bioerodible polymer is based primarily on the known properties of the polymer such as polymer strength, rate of hydrolytic degradation, etc. One of ordinary skill in the art may take these and/or other properties into account in selecting a particular polymer for a particular application. Thus, such a selection of a particular polymer is within the skills of the ordinary skilled practitioner.

The second bioerodible polymer of the disclosed semi-IPN alloy may be of a type that undergoes hydrolysis to produce acidic products when exposed to an aqueous medium, such as polydioxanone, poly(ϵ -caprolactone); polyanhydrides; poly(ortho esters); copoly(ether-esters); polyamides; polylactones; polypropylene fumarates; and combinations thereof. However, the second bioerodible polymer, preferably upon crosslinking, additionally provides the biopolymeric scaffolding or internal reinforcement which gives the bioerodible polymeric semi-IPN alloy its superior mechanical

- 8 -

properties. (As such, the second polymer is desirably different from the first.) This scaffolding is desirably obtained by crosslinking the second bioerodible polymer. Crosslinking may take place, e.g., in a bone cement shortly before or after the cement ingredients have been introduced to the bone fissure or junction. When making an alloy material for IFDs crosslinking may be effected: a) with the first and second bioerodible polymers in cosolution via chemical crosslinking or by irradiation (e.g., γ -irradiation); b) by melt mixing the first and second bioerodible polymers, then irradiating to crosslink the second bioerodible polymer; or c) by forming the biopolymeric scaffolding first via chemical crosslinking or by irradiation, then impregnating the scaffolding with the first bioerodible polymer.

In an advantageous embodiment the second bioerodible polymer comprises polypropylene fumarate, which may be desirably crosslinked using vinyl monomers such as vinyl pyrrolidone (VP). An advantage of VP crosslinking of PPF is that the crosslinks terminate at hydrolytically labile fumarate ester bonds, making the crosslinked network hydrolytically degradable. Furthermore, the hydrolysis products are highly soluble and hence the scaffolding (and thus the entire alloy) is truly resorbable. The crosslinking reaction should preferably seek to minimize homopolymer formation. Other crosslinking monomers such as methyl methacrylate (MMA) may also be used as long as bioerodibility is not compromised. A high PPF:VP ratio favors crosslinking; because the crosslinking reaction is carried out in solution, low concentrations of VP may be used. The degree of crosslinking necessary to form the scaffolding will depend on the particular application, i.e., the relative hardness or rigidity desired, but generally crosslinking of about 5% to 50% of the available crosslinking sites is acceptable, more particularly 5% to 30%.

- 9 -

5 The bioerodible material of the invention may include a buffering compound which may be a base or base-containing material capable of reacting with the acidic products generated upon hydrolysis of the bioerodible polymer. Since
10 the bioerodible polymers undergo hydrolysis in the body and generate acidic products that cause irritation, inflammation, and swelling (sterile abscess formation) in the treated area, the inclusion of buffer in the bioerodible material counteracts this effect by neutralizing the acidic
15 degradation products and thereby reducing the sterile abscess reaction. The buffer included in the bioerodible material of the invention maintains the pH surrounding the area of surgery to approximately neutrality (i.e., pH 7), or any other pH chosen by the surgeon. Preferably, the pH is maintained in the range of 6-8, and more preferably in the range of 6.8-7.4.

Exemplary buffering materials include inorganic acid salts, organic acid salts, or polymeric organic acid salts. Preferably, the calcium salts of weak acids are used, such
20 as calcium carbonate, although calcium phosphate, calcium acetate, calcium citrate, calcium succinate, and calcium gluconate may also be used. Polymeric buffers may also be used as buffering compounds according to the invention. Suitable polymeric buffers preferably include basic groups
25 which neutralize the acidic products generated upon hydrolysis of the bioerodible polymer. Such polymeric buffers include hydrolytically stable polymers, such as polyamines, poly(N-vinyl carbazole), poly(N-vinyl pyrrolidone), poly(acrylic acid), poly(acrylamide), or a
30 copolymer based on acrylic acid. Another class of buffering compounds useful in the materials and methods of the invention are compounds which, on exposure to water, hydrolyze to form a base as one reaction product. The generated base is free to neutralize the acidic products produced upon hydrolysis of the bioerodible polymer.
35 Compounds of this type include aryl or alkyl carbamic acids

- 10 -

and imines. The base-generating compounds used according to the invention offer the advantage that the rate of hydrolysis of the base generator may be selected to correlate to the rate of hydrolysis of the bioerodible polymer.

5 The inclusion of soluble buffering materials such as those disclosed herein (such as a combination of citric acid and sodium bicarbonate; calcium acetate, and calcium gluconate) also have an important second function *in vivo*.
10 Upon exposure to aqueous media such as tissue fluids these compounds dissolve almost immediately, leaving pores in the material, whether it be a cement or IFD. (In the case of the citric acid and sodium bicarbonate combination, upon exposure to water *in vivo* to form CO₂ and water, leaving holes in place of the solid chemical.) These pores facilitate bone
15 cell migration into the device or cement, and thus serve as osteoconductive pathways for bone healing. Pore size may be controlled by controlling the size of the soluble material introduced to the alloy, i.e., by grinding and sieving the filler to select the appropriate particle size range.

20 The development of such pores is illustrated in Figures 1A and 1B, which are SEM (Amray AMR-1000 SEM at 6250x) of a bone cement alloy containing crosslinked PPF scaffolding and PLGA/calcium gluconate after one and two weeks exposure to water. The alloy was subjected to conditions similar to
25 placement *in vivo*, over a period of weeks. The development of pores in the alloy, where none were detectable at the start of the experiment, is seen. The holes measure about 3-6 microns on average, but larger holes of 10-15 microns were also seen.

30 It has been surprisingly found that a combination of a calcium carbonate and hydroxyapatite has been found to support osteoconductivity and osteoinductivity, i.e., providing a pathway for bone cells to penetrate, as well as inducing movement of bone cells into those pathways, as a way

- 11 -

of promoting bony ingrowth as resorption of the alloy progresses.

5 Other fillers may be included in the alloy (preferably protected by the first bioerodible polymer, as disclosed herein) as alternatives to fillers like calcium carbonate and hydroxyapatite, such as ground, demineralized bone and/or unprocessed cadaver allogenic bone.

10 The buffering compound preferably has an acid dissociation constant (K_a) that is smaller than the acid dissociation constant of the acidic products generated upon hydrolysis of the bioerodible polymer. Alternatively, the buffering compound preferably has a hydrolysis constant that is greater than the hydrolysis constant of the acidic products. Further, the buffering compound preferably is only
15 partially soluble in an aqueous medium. In general, buffers of lower solubility are preferred because buffer loss from the polymer by diffusion will be minimized. Details of determining appropriate buffers, methods and amounts of addition, etc., are disclosed in further detail in pending
20 US patent application 08/626,521, the disclosure of which is incorporated herein by reference.

The semi-IPN alloy of the invention has mechanical properties comparable to human bone, as set forth in Table 1.

- 12 -

Table 1

Stiffness,		GPa	1-30
Bending:	Modulus Strength,	GPa	6-30 ⁽¹⁾
		MPa	160
Torsion:	Modulus Strength,	GPa	3.2 (femur)
		MPa	54.1 (femur)
Tension:	Modulus Strength,	GPa	14.9-18.9
		MPa	124-174
Compression:	Modulus Strength,	GPa	8-9 ⁽²⁾
		MPa	170 (femur)

(1) Poly(L-lactide) and Poly(D,L-lactide) reinforced with calcium phosphate fibers

(2) Equine long bones

Methods of making a bioerodible material for implantation into a surgical site are further contemplated by the inventors. In one embodiment, the first and second bioerodible polymers (and optional components such as biologically active agents for release into surrounding bone tissue and buffering compounds) are dissolved in solvent and mixed to homogeneity, after which the second bioerodible polymer is treated to create the biopolymeric scaffolding, e.g., by crosslinking. The resulting mixture is cast into a desired form, e.g., a sheet, film, plate, screw, etc., and the solvent is evaporated to produce a (buffered) bioerodible implantable material in film form. The product may be further processed, for example, compacted under pressure, extruded through a die, injection molded, or shaped into a form useful for bone repair. Techniques such as compression

- 13 -

molding may be used to form end-use configurations such as screws, plates, etc.; or stock from which IFDs may be machined. A constant pressure hydraulic press such as the Compac Model MPC-40 may be used for molding.

5 In another embodiment the alloy may be prepared similar to methods disclosed in U.S. Patent No. 5,456,917 to Wise et al., the text of which is incorporated by reference herein, wherein a bioerodible polymer foam scaffolding is prepared by lyophilization of solutions of the polymer in a suitable
10 solvent, such as glacial acetic acid or benzene. A solution containing the first bioerodible polymer and other ingredients such as active agents, buffers, etc. are then forced into the void volume of the scaffolding by cycles of evacuation (degassing) and repressurization. Solvents for
15 the first bioerodible polymer and active agent include water and other solvents which do not dissolve the first bioerodible polymer or change its structure or morphology, such as the lower alcohols. The solvent is then removed by a second lyophilization, and the resulting alloy may be
20 further processed.

The invention also relates to bioerodible bone cements for both orthopaedic repair and for controlled release of a biologically active agent in, if necessary, a protecting polymeric envelope. The bone cement and method of making it
25 encompasses a range of cement materials, the properties of which depend upon the concentration of components to enable preparation of cements of initial (precure) low viscosities which can be delivered by injection to its intended site or cements of higher viscosity which may be molded, e.g., as a
30 putty, to fractures or surgical sites of complex topography.

The first bioerodible polymer, as noted above, may be loaded with an active agent to provide a controlled release of the active agent as the alloy is resorbed. Control of the release rate is achieved by incorporating the active agent
35 in a protecting envelope of the first bioerodible polymer.

- 14 -

In addition, further control of the release rate is achieved by incorporating non reactive fillers of varying solubility (such as hydroxyapatite) into the alloy. Any type of active agent may be incorporated into the first bioerodible polymer, including without limitation drugs, hormones, antibiotics, cells etc.

The bone cement of the invention comprises the first and second bioerodible polymers as set forth herein. Other desirable components of the cement include biologically active or therapeutic agent(s), cross linking agent (such as a vinyl monomer); an initiator for the cross linking reaction between the second bioerodible polymer and the crosslinking agent; and accelerator(s) and inhibitor(s) to control the cure kinetics. Further components of the material of the invention include biologically inert solid fillers, liquid (aqueous or non-aqueous) diluents for viscosity control and for solubilization of components, and wetting agents (surface active agents or detergents) to facilitate mixing of components and contact of the mixed components with tissue.

The cement may be advantageously prepared as a two or three part formulation, in which the initiator and accelerator, or initiator and components for forming the scaffolding, e.g., second bioerodible polymer and crosslinker, are kept separate until the parts are combined. The combined parts are allowed to cure *in situ* (at the surgical or fracture site) to aid in maintaining fracture reduction or to fill defects or other openings in bone following surgery. Keeping the system parts separate prior to use ensures against premature reaction, to increase pre-use stability and shelf life.

In a preferred embodiment the second bioerodible polymer is PPF, which is crosslinked polymerization between PPF and a vinyl monomer such as vinyl pyrrolidone or methyl methacrylate. The vinyl polymerization employs an initiator such as benzoyl peroxide; other initiators may be used.

- 15 -

Accelerators such as N,N-dimethyl-p-toluidine (DMPT) and inhibitors such as hydroquinone (HQ) or t-butylhydroquinone (TBHQ) may also be included to control cure reaction kinetics. Other components such as detergents and water may be included as processing aids to adjust viscosity and to improve workability of the cement.

The composition of the cement may be varied according to requirements of cure time, viscosity, loading of biologically active or therapeutic agent(s), and degradation rates. Component ranges (range 2 = particularly preferred range) are given in Table 2.

Table 2

<u>Component</u>	<u>Range 1 (%wt)</u>	<u>Range 2 (wt%)</u>
First bioerodible polymer	0-50	3-15
Second bioerodible polymer	5-60	30-50
Cross linking agent	5-50	8-12
Therapeutically inert liquid diluent	0-50	10-20
Active agent protected by first bioerodible polymer	1-50	
Initiator	0-5	0.5-1.5
Inhibitor	0-5	
Accelerator	0-5	
Water	0-1	
Detergent	0-1	
Soluble buffering material	--	3-12
Less soluble buffering material/osteoinductive agent	--	5-20

One embodiment of a two part system is comprised as follows:

Part A	Part B
PPF	Inert Fillers
Vinyl Monomer	PLGA/biologically active or therapeutic agent(s)
Accelerator	Initiator
Diluents	Inhibitor

This two part formulation 1) separates the polymerizable components from the initiator; and 2) separates the protected biologically active or therapeutic agent(s) from the liquid components, which prevents premature release of the

- 16 -

biologically active or therapeutic agent(s) from the first bioerodible polymer.

A typical embodiment of a three part system is shown below.

5	Part A	Part B	Part C
	PPF	Initiator	Inert Fillers
	Vinyl Monomer	Diluents	Accelerator
	Inhibitor		PLGA/biologically active or therapeutic agent(s)

10 An advantage of the three part formulation is that it separates the biologically active or therapeutic agent(s) from the initiator, which is the least thermally stable component of the cement.

15 Incorporation of into the first bioerodible polymer provides several advantages for the controlled release feature of the invention. The first bioerodible polymer, such as PLGA, functions as a protective coating to prevent the biologically active or therapeutic agent(s) from reacting with the components of the cement. Thus it is possible to
20 maintain the full potency of the biologically active or therapeutic agent(s) during the cure process. In addition, possible reactions of the biologically active or therapeutic agent(s) with the free radicals generated during the curing process is minimized because the time during which the cement
25 changes from a fluid or viscous putty to a hard mass is short (about ten minutes). The first bioerodible polymer also functions to moderate the release of the biologically active or therapeutic agent(s).

EXAMPLE 1

30 Several experiments were conducted to demonstrate PPF crosslinking with vinyl pyrrolidone (VP) in glacial acetic acid (gl HAC) solution in the presence of PLGA-85:15. gl HAC is a suitable solvent for several reasons: 1) traces remaining in the product will not be toxic; 2) its vapor
35 pressure at its freezing point is high (FP = 16.7°C; VP at 17.5°C = 10 mm Hg). This property allows formation of alloys

- 17 -

of the disclosure by lyophilization to remove the solvent. The following samples were prepared as shown in Table 3.

Table 3

-	39-1	39-2	40-1	40-2	40-3	41-1
PLGA, g	---	---	---	---	---	0.350
PPF, g	0.979	0.999	0.979	0.998	0.956	0.954
VP, g	2.267	2.000	2.165	2.165	2.190	2.167
B P , g(1)	0.134	1.381	0.136	0.139	0.134	0.139
gl HAC, ml	10	10	10	10	10	10
R x T°C(2)	90	90	RT	70	60	70
R x t min(2)	25	10	6 mos	31	100	30-40

(1) BP = benzoyl peroxide

(2) Rx T°C; Rx t min = reaction temperature and time

Prior to heating, all samples were completely dissolved in gl HAC. After heating at the temperature and for the time indicated, a continuous solid phase had formed in all samples. Solubility tests on these samples indicated that crosslinking preferentially occurred over PVP homopolymer formation. Lyophilization of PPF/VP/BP and PLGA/PPF/VP/BP crosslinked in gl HAC results in porous solids.

The following describes an exemplary procedure for preparing a bioerodible semi-IPN alloy in accordance with the invention.

(a) Removal of NaOH Inhibitor from VP. VP (1-vinyl-2-pyrrolidone, Aldrich lot 07401BQ) contained 1% inhibitor of NaOH. Separation of NaOH from the VP was accomplished by a vacuum distillation of the VP/NaOH solution. The distilled VP was collected by condensing VP vapor with cold water, while the NaOH was left in the distillation flask.

(b) Crosslinking of PPF (X-PPF) with VP in Glacial Acetic Acid. At room temperature, 1.0g PPF [CSI, lot 48-86-2, Mw. 7277] and 1.1g DVP were co-dissolved in 10ml

- 18 -

5 gl HAC (Fisher lot 905039) in a lyophilization flask. 0.13g of a preground BP powder (Aldrich lot 06428CW) was then added to the solution in the flask. After the BP dissolved completely, the solution showed a clear amber color. The lyophilization flask was placed in a preheated silicon oil bath with a temperature of 773°C. After 15 minutes in the bath, the solution started turning white and cloudy, indicating crosslinking. After another 5 minutes in the bath, the solution became a pale yellow "jelly." The flask was then removed from the bath to a freezer with a temperature of -10°C. The flask was stored in the freezer for over 12 hours before it was lyophilized.

15 (c) Lyophilization of X-PPF/GlHAc Solution. The lyophilization flask, now containing the frozen X-PPF/GlHAc solution, was placed in an ice bath and was connected to a lyophilization setup which consisted of a solvent trap and a reduced pressure at 1mm Hg. The lyophilization proceeded until all the GlHAc was collected in the trap.

20 (d) Removal of Unreacted VP and PVP. The removal of unreacted compounds was accomplished by impregnating the foam with water by successive cycles of evacuation and admission of air. The washed foam was dried in an oven with a temperature set at 50°C.

25 (e) Impregnation of X-PPF Foam Scaffolding with PLGA: PLGA-85:15 (PLGA-85:15, B.I. lot 25024, Mw 11500.) was introduced by immersing the foam in a solution of PLGA in GlHAc, evacuating to remove air from the foam and repressurizing to force the PLGA solution into the foam scaffolding. A second lyophilization was used to remove the GlHAc, leaving the PLGA in the scaffolding. The ratio of PLGA deposited to the foam was 52.4 w/w%.

30

35

- 19 -

The product was desirably washed with water to extract any PVP that has been formed. IFDs may be formed from the material as disclosed herein.

EXAMPLE 2

5 High viscosity cements or putties according to the disclosure using VP crosslinker were prepared as a two part formulation of variable composition, as shown in Table 4, which presents the weights of the components and the weight fractions of the PPF, calcium phosphate and VP.

- 20 -

TABLE 4

Composition of Cement Formulations

Composition(g)

Weight Fraction

Sample	PPF*	CP	VP	BP	DMPT/ VP†	f(PPF)	f(CP)	f(VP)
45-75-1	1.0012	0.0000	1.0006	0.0604	0.0000	0.4855	0.0000	0.4852
45-75-2	1.0000	0.0000	0.6004	0.0604	0.0000	0.6022	0.0000	0.3616
45-75-3	1.0000	0.0000	1.0070	0.0000	0.0026	0.4831	0.0000	0.4877
45-87-2A	1.0000	1.0007	1.0012	0.0605	0.0028	0.3262	0.3265	0.3275
45-87-2B	1.0007	0.9997	1.0009	0.0607			0.3261	0.3276
45-110-1	1.0003	1.0001	0.5029	0.0605			0.3893	0.1978
45-110-2	1.0000	1.0004	2.0024	0.0606			0.2460	0.4932
45-110-3	1.0000	1.0001	2.9996	0.0603			0.1974	0.5933
45-132-1	1.0005	1.0000	1.5049	0.0605			0.2801	0.4227
45-132-2	1.0000	1.0001	2.4998	0.0600			0.2190	0.5489
45-123-3	1.0000	1.0007	3.0005	0.0605			0.1976	0.5930

* PPF sample 48-86-2, $M_w = 6651$; $M_n = 2587$, polydispersity

† Concentration of DMPT in VP = 0.48% (w/w)

- 21 -

Components of Parts A and B are summarized below:

Part A: PPF (Wt. Avg. Mol. Wt. = 6650, polydispersity = 2.57)

5 Tribasic calcium phosphate (hydroxyapatite)
(approximately $\text{Ca}_{10}(\text{OH})_2(\text{PO}_4)_6$)

Vinyl pyrrolidone (cross linking vinyl monomer)

N,N-Dimethyl-p-toluidine (accelerator)

Part B: Vinyl Pyrrolidone

10 Benzoyl peroxide (initiator)

hydroquinone (inhibitor)

15 Samples were cured in sealed vials. After curing the samples were ground, weighed, washed with water to extract soluble components, and dried to constant weight. The remaining insoluble material was then extracted with tetrahydrofuran to remove uncrosslinked PPF. In all cases almost all of the PPF was crosslinked: >98% in 6 out of 9 samples, and > 86% in the remaining three samples. Further, the percent of PPF crosslinked was independent of composition, i.e., independent of filler, accelerator, initiator, or monomer. On the other hand, the fraction of VP which was incorporated into the scaffolding depended strongly on the ratio of PPF/VP, increasing with increasing PPF/VP ratio. The ratio of VP incorporated into the crosslinks varied linearly with the PPF/VP ratio. These results are summarized in Table 5 and presented graphically in Figures 2 and 3. The significance of these results can be appreciated if we define two quantities. The density of crosslinks between PPF chains can be defined as $dcl = (\text{moles of crosslinks/mole of PPF})$ and the average length of crosslinks can be defined as $lcl = (\text{moles of VP/mole of PPF})$. Thus $(dcl)(lcl) = (\text{mole of VP/mole of PPF})$. Thus by varying the PPF/monomer ratio, control of the product $(dcl)(lcl)$ can be exercised.

35

TABLE 5

Fraction of VP and PPF Incorporated into Crosslinked PPF
and Distribution of VP between XL-PPF and PVP

Sample	PPF/V P	F_f	F_p	F. Mean \pm SD [‡]	F_{ppf}	F_{pp}
45-75-1	1.0006	0.5554	0.5007	0.5281 ± 0.0387	0.9941	1.0038
-2	1.6656	0.7097	0.6332	0.6715 ± 0.0541	0.9858	1.7260
-3	0.9905	0.5725	0.5127	0.5426 ± 0.0423		1.0519
-87-2A	0.9960	0.4649	0.5463	0.5056 ± 0.0576	0.8571	1.2042
87-2B	0.9966	0.4727	0.4349	0.4538 ± 0.0267	0.9773	0.7695
-110-1	1.9693		0.4970	0.4970		
-2	0.4985	0.2206	0.2472	0.2314 ± 0.0153	0.9937	0.3196
-3	0.3326	0.2222	0.2449	0.2336 ± 0.0161	0.8714	0.3243
-132-1 0	0.5663 0	0.3272	0.3764	0.3518 ± 0.0348	0.8656	0.6035
-2	0.3989	0.2893	0.2747	0.2820 ± 0.0103	0.9812	0.3787
-3	0.3330	0.2238	0.2634	0.2486 ± 0.0209	0.9953	0.3297

⇒ Fraction of VP in XL-PPF calculated by material balance based on PPF.

† Frace of VP in XL-PPF calculated by material balance based on VP.

‡ F = mean \pm standard deviation of F | and F_p (mean $F_{ppf} = 0.9469 \pm 0.0619$).

§ Fraction of PPF which is crosslinked.

| Distribution of VP between XL-PPF and PVP.

- 23 -

Varying the PPF/monomer ratio will also vary the viscosity of the cement if the crosslinking monomer is the only liquid component. However, the viscosity may be controlled independently as described by various diluents which may be liquid to reduce viscosity or solid fillers, such as tribasic calcium phosphate (hydroxyapatite), to increase viscosity.

EXAMPLE 3

A low viscosity injectable cement may be formulated using VP both for cross linking PPF, and to control the initial viscosity. The cement can also be reformulated by substituting one of several acceptable solvents for part of the VP. In this example, this change is in Part B, which contains no monomer (VP). Acceptable solvents include propylene glycol, poly(ethylene glycol), and peanut oil. Cure rate and hardness are not compromised by this substitution. The advantages of this substitution are threefold. First, VP is miscible with these solvents as well as with water. By creating a more lipophilic environment the rate at which VP diffuses from the injection site is diminished, thus allowing a greater portion to be incorporated into the scaffolding. Minimizing diffusion into surrounding tissue is expected to diminish inflammatory response. A second advantage is that being more dilute, the probability of crosslinking with PPF is increased and that of homopolymer formation is reduced. A third advantage is increased stability. The initiator, included in Part B is now dissolved in PO rather than in the monomer VP thus eliminating premature polymerization in that part. The formulations are given in Table 6.

In this example peanut oil has been used to replace a portion of the VP, and accounts for 50% by weight of the liquid components. The Shore D hardness of IC's formulated with PO were measured as 45-50. This is comparable to polystyrene, 65; poly(ethylene), 40; and PTFE, 50.

- 24 -

Table 6

COMPOSITION OF REFORMULATED INJECTABLE BONE CEMENT (Weight %)

5		Part A	Part B
		PPF 37.1	PO 25.1
		VP 25.0	BP 0.6
		CaAc2 12.0	
		DMPT 0.2	
10	PPF	= poly(propylene fumarate)	
	VP	= vinyl pyrrolidone (crosslinking agent)	
	CaAc2	= calcium acetate (soluble filler)	
	DMPT	= dimethyl-p-toluidine (accelerator)	
15	BP	= benzoyl peroxide (initiator)	
	PO	= peanut oil (diluent)	

The initial (precure) viscosity of the reformulated cement is determined by both the solids to liquid ratio and the viscosities of the fluid components (VP and PO). More important than the actual viscosity value is the force a surgeon must exert on the piston of a syringe containing the cement in order to expel it. To evaluate this flow rates of glycerol, peanut oil, and the injectable cement through a syringe equipped with a 15 gauge (0.137 cm i.d.) by 1.5" (3.81 cm) length were measured. Pressure on the piston was applied with weights of 0.5, 1.0, and 2.0 kg and flow of a given volume was timed. Mean flow rates under a given force are indicated in Table 7.

Table 7

MEAN FLOW RATES (cm³/sec)

Weight on Piston (kg)	Pressure (gram/cm ²)	Flow Rates, cm ³ /sec		Peanut Oil
		Glycerol	Cement	
0.5	283	0.001	0.001	---
1.0	566	0.054±0.003	0.169±0.034	---
2.0	1132	0.145±0.008	0.342±0.012	2.59±0.22

The pressure exerted by these weights, calculated by dividing the weight by the cross sectional area of the syringe barrel, are easily achieved by normal thumb pressure. The slow flow

- 25 -

rates observed at 0.5 kg is due to the frictional resistance of the piston. Exerting the highest pressure (1132 g/cm²), 5 cc of cement can be delivered in less than 15 seconds.

EXAMPLE 4

5 The effect of temperature and accelerator on cure time in injectable bone cements in accordance with the invention was studied. The mixture of Example 3 was used with the following changes. VP may be used as an alternative to the crosslinking agent methyl methacrylate (MMA) and propylene glycol may be used as a solvent for PPF or as a diluent. Calcium phosphate tribasic (hydroxyapatite, "HA") is used as an relatively insoluble filler. The initiator is benzoyl peroxide and was used without an accelerator. In this example, reaction at room temperature is slow, but increases when heat is applied. In all cases the formulations are sufficiently liquid for injection. The data are shown in Table 8.

20 The formulations may also be varied by including an accelerator in either part A or part B, and an initiator in the other part. A soluble filler may also be included. In the examples given in Table 9 no non-reacting solvent is used. Liquid monomer (MMA or VP) but no PG is used in these formulations. The soluble filler calcium acetate (CaAc₂) is used in place of HA. Cure proceeds rapidly at room temperature with VP but more slowly when MMA is substituted for VP. The location of the initiator may be in either Part A or Part B as long as the accelerator is in the other part, with no effect on stability (when stored cold) or reaction rates. Table 9 describes these formulations. All pre-cure viscosities are sufficiently low for injection.

- 26 -

Table 8: Injectable Cements Using Propylene Glycol as a Non-Reacting Solvent: No Accelerator

Experiment	1	2	3	4	5	6
Part A						
5 PPF:PG = 1:1*, ml	1.0	1.0	1.0	1.0	1.0	0.30
HA, gram	0.2	0.2	0.4	0.4	0.6	0.25
Part B						
VP:BP = 1.0:0.5**, ml	1.0	0.5	0.5	0.5	0.4	0.12
Temperature, °C	71	71	71	36	71	71
10 Cure Time, min.	2	2	1	19(hr)	2.5	2.5
* 1.0 gram PPF/1.0 ml PG						
** 1.0 ml VP/0.5 gram BP						

15

Table 9: Injectable Cements with Accelerator and Soluble Filler: No Solvent or Diluent

Experiment	A	B	1	2
Part A				
20 PPF*, gram	1.50	1.00	1.50	1.50
VP, gram	1.00	---	---	1.00
MMA, gram	---	1.78	1.00	---
CaAc2, gram	0.10	1.60	0.10	0.50
BP, gram	----	0.15	---	---
25 DMPT, gram	0.01	---	0.01	0.01
Part B				
VP, gram	0.50	---	---	0.50
MMA, gram	---	0.34	0.50	---
BP, gram	0.025	---	0.025	0.025
30 DMPT, gram	---	0.016	---	---
Cure time, minutes	0.3-0.5	>10	>10	0.5

35

Having disclosed the preferred embodiments, those skilled in the art will realize many variations are possible which will still be within the spirit and scope of the claimed invention. Therefore, it is the intention to limit the invention only as indicated by the scope of the claims.

- 27 -

CLAIMS*What is claimed is:*

1. A bioerodible polymeric semi-IPN alloy comprising
 - a) a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation; and
 - b) a second bioerodible scaffolding polymer which provides a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy.
2. The bioerodible polymeric semi-IPN alloy of claim 1 further comprising a buffering compound that buffers said acidic products within a desired pH range.
3. The bioerodible polymeric semi-IPN alloy of claim 1 wherein said biopolymeric scaffolding is obtained by crosslinking said second bioerodible polymer.
4. The bioerodible polymeric semi-IPN alloy of claim 1 wherein said second bioerodible polymer comprises polypropylene fumarate (PPF) which is cross-linked to form said biopolymeric scaffolding.
5. The bioerodible polymeric semi-IPN alloy of claim 4 wherein said PPF is crosslinked by a vinyl monomer.
6. The bioerodible polymeric semi-IPN alloy of claim 5 wherein said vinyl monomer is vinyl pyrrolidone.
7. The bioerodible polymeric semi-IPN alloy of claim 4 wherein said PPF is crosslinked by methyl methacrylate (MMA).
8. The bioerodible polymeric semi-IPN alloy of claim 1 further comprising a biologically active or therapeutic agent.

- 28 -

9. The bioerodible polymeric semi-IPN alloy of claim 1 wherein said biologically active or therapeutic agent is selected from the group consisting of bone repair proteins, antibiotics, cells, and mixtures thereof.

10. The bioerodible polymeric semi-IPN alloy of claim 1 wherein said first bioerodible polymer is different from said second bioerodible polymer.

11. The bioerodible polymeric semi-IPN alloy of claim 1 wherein said first bioerodible polymer is selected from the group consisting of poly(lactide-co-glycolide) (PLGA); polydioxanone; poly(ϵ -caprolactone); polyanhydrides; poly(ortho esters); copoly(ether-esters); polyamides; polylactones; polypropylene fumarates ($\text{H}[-\text{O}-\text{CH}(\text{CH}_3)-\text{CH}_2-\text{O}-\text{CO}-\text{CH}=\text{CH}-\text{CO}-]_n\text{OH}$); and combinations thereof.

12. The bioerodible polymeric semi-IPN alloy of claim 2 wherein said buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of inorganic acid salts; organic acid salts; and polymeric organic acid salts.

13. The bioerodible polymeric semi-IPN alloy of claim 2 wherein said buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of citric acid and sodium bicarbonate; calcium carbonate; calcium phosphate; calcium acetate; calcium citrate; calcium succinate; hydrolyzable polyamines; poly(N-vinyl carbazole); poly(acrylic acid); poly(acrylamide); and mixtures thereof.

14. The bioerodible polymeric semi-IPN alloy of claim 13 wherein said buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of calcium carbonate, calcium phosphate, calcium

- 29 -

acetate, calcium citrate, calcium succinate, and mixtures thereof; said alloy further comprising an osteoinductive composition.

15. The bioerodible polymeric semi-IPN alloy of claim 14 wherein said the particle size of said buffering compound is from about 5μ to 500μ .

16. The bioerodible polymeric semi-IPN alloy of claim 14 wherein said osteoinductive composition comprises hydroxyapatite.

17. The bioerodible polymeric semi-IPN alloy of claim 1, said alloy having the mechanical properties set forth in Table 1.

18. A bioerodible internal fixation device made from a bioerodible polymeric semi-IPN alloy comprising

- a) a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation; and
- b) a second bioerodible scaffolding polymer which provides a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy.

19. The bioerodible internal fixation device of claim 18 further comprising a buffering compound that buffers said acidic products within a desired pH range.

20. The bioerodible internal fixation device of claim 18 wherein said biopolymeric scaffolding is obtained by crosslinking said second bioerodible polymer.

21. The bioerodible internal fixation device of claim 18 wherein said second bioerodible polymer comprises polypropylene fumarate (PPF) which is cross-linked to form said biopolymeric scaffolding.

- 30 -

22. The bioerodible internal fixation device of claim 18 wherein said vinyl monomer is vinyl pyrrolidone.

23. The bioerodible internal fixation device of claim 18 further comprising a biologically active or therapeutic agent.

24. The bioerodible internal fixation device of claim 18 wherein said first bioerodible polymer is different from said second bioerodible polymer.

25. The bioerodible internal fixation device of claim 18, said alloy having the mechanical properties set forth in Table 1.

26. A method of forming a bioerodible polymeric semi-IPN alloy, comprising the steps of

- a) forming a cosolution of a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation, and a second bioerodible scaffolding polymer;
- b) crosslinking said second bioerodible scaffolding polymer to form a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy;
- c) removing the cosolution solvent to provide a non-compacted semi-IPN alloy; and
- d) compacting said non-compacted semi-IPN alloy to form a compacted mass.

27. The method of claim 26 further comprising the step of extruding said compacted mass into the shape of an IFD.

28. The method of claim 26 wherein said compacted mass is machined to the shape of an IFD.

- 31 -

29. The method of claim 26 wherein said cosolution further comprises crosslinking monomer and crosslinking initiator.

30. The method of claim 26 wherein said second bioerodible polymer comprises polypropylene fumarate (PPF).

31. The method of claim 26 wherein said PPF is crosslinked by a vinyl monomer.

32. The method of claim 26 wherein said vinyl monomer is vinyl pyrrolidone.

33. The method of claim 26 wherein said first bioerodible polymer is different from said second bioerodible polymer.

34. The method of claim 26 wherein said first bioerodible polymer is selected from the group consisting of poly(lactide-co-glycolide) (PLGA); polydioxanone; poly(ϵ -caprolactone); polyanhydrides; poly(ortho esters); copoly(ether-esters); polyamides; polylactones; polypropylene fumarates ($\text{H}[-\text{O}-\text{CH}(\text{CH}_3)-\text{CH}_2-\text{O}-\text{CO}-\text{CH}=\text{CH}-\text{CO}-]_n\text{OH}$); and combinations thereof.

35. The method of claim 26, wherein said alloy has the mechanical properties set forth in Table 1.

36. A method of forming a bioerodible polymeric semi-IPN alloy, comprising the steps of

- a) forming a cosolution of a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation, and a second bioerodible scaffolding polymer;
- b) crosslinking said second bioerodible scaffolding polymer to form a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy;

- 32 -

- c) removing the cosolution solvent to provide a non-compacted semi-IPN alloy; and
- d) compacting said non-compacted semi-IPN alloy to form a compacted mass.

5

37. The method of claim 36 further comprising the step of extruding said compacted mass into the shape of an IFD.

10

38. The method of claim 36 wherein said compacted mass is machined to the shape of an IFD.

39. The method of claim 36 wherein said cosolution further comprises crosslinking monomer and crosslinking initiator.

15

40. The method of claim 36 wherein said second bioerodible polymer comprises polypropylene fumarate (PPF).

41. The method of claim 36 wherein said PPF is crosslinked by a vinyl monomer.

20

42. The method of claim 36 wherein said vinyl monomer is vinyl pyrrolidone.

25

43. The method of claim 36 wherein said first bioerodible polymer is different from said second bioerodible polymer.

30

44. The method of claim 36 wherein said first bioerodible polymer is selected from the group consisting of poly(lactide-co-glycolide) (PLGA); polydioxanone; poly(ϵ -caprolactone); polyanhydrides; poly(ortho esters); copoly(ether-esters); polyamides; polylactones; polypropylene fumarates ($\text{H}[-\text{O}-\text{CH}(\text{CH}_3)-\text{CH}_2-\text{O}-\text{CO}-\text{CH}=\text{CH}-\text{CO}-]_n\text{OH}$); and combinations thereof.

35

45. The method of claim 36, wherein said alloy has the mechanical properties set forth in Table 1.

- 33 -

46. The method of claim 36 further comprising the step of extruding said compacted mass into the shape of an IFD.

5 47. The method of claim 36 wherein said compacted mass is machined to the shape of an IFD.

48. A method of forming a bioerodible polymeric semi-IPN alloy, comprising the steps of

10 a) melt mixing together a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation, and a second bioerodible scaffolding polymer;

15 b) crosslinking said second bioerodible scaffolding polymer by irradiation to form a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy;

c) allowing the product of steps a) and b) to cool and form a non-compacted semi-IPN alloy; and

20 d) compacting said non-compacted semi-IPN alloy to form a compacted mass.

49. The method of claim 48 further comprising the step of extruding said compacted mass into the shape of an IFD.

25 50. The method of claim 49 wherein said compacted mass is machined to the shape of an IFD.

30 51. A two part bioerodible bone cement system which, upon mixing of the system parts, forms a bioerodible polymeric semi-IPN alloy, consisting of

35 a) a first part comprising a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation; crosslinking initiator; and a therapeutically effective amount of a biologically active or therapeutic agent; and

- 34 -

b) a second part comprising a second bioerodible scaffolding polymer which upon crosslinking provides a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy; and crosslinking agent for said second bioerodible scaffolding polymer.

52. The bone cement system of claim 51 further comprising in one of said parts a buffering compound that buffers said acidic products within a desired pH range.

53. The bone cement system of claim 51 wherein said second bioerodible polymer comprises polypropylene fumarate (PPF).

54. The bone cement system of claim 53 wherein said crosslinking agent is a vinyl monomer.

55. The bone cement system of claim 54 wherein said crosslinking agent is vinyl pyrrolidone.

56. The bone cement system of claim 53 wherein said crosslinking agent is methyl methacrylate (MMA).

57. The bone cement system of claim 51 further comprising in one of said parts a biologically active or therapeutic agent.

58. The bone cement system of claim 57 wherein said biologically active or therapeutic agent is selected from the group consisting of bone repair proteins, antibiotics, cells, and mixtures thereof.

59. The bone cement system of claim 51 wherein said first bioerodible polymer is different from said second bioerodible polymer.

- 35 -

60. The bone cement system of claim 51 wherein said first bioerodible polymer is selected from the group consisting of poly(lactide-co-glycolide) (PLGA); polydioxanone; poly(ϵ -caprolactone); polyanhydrides; poly(ortho esters);
5 copoly(ether-esters); polyamides; polylactones; polypropylene fumarates $(H[-O-CH(CH_3)-CH_2-O-CO-CH=CH-CO-]_nOH)$; and combinations thereof.

61. The bone cement system of claim 52 wherein said
10 buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of inorganic acid salts; organic acid salts; and polymeric organic acid salts.

62. The bone cement system of claim 52 wherein said
15 buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of citric acid and sodium bicarbonate; calcium carbonate; calcium phosphate; calcium acetate; calcium citrate; calcium
20 succinate; hydrolyzable polyamines; poly(N-vinyl carbazole); poly(acrylic acid); poly(acrylamide); and mixtures thereof.

63. The bone cement system of claim 52 wherein said
25 buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of citric acid and sodium bicarbonate; calcium carbonate, calcium phosphate, calcium acetate, calcium citrate, calcium succinate, and mixtures thereof; said alloy further comprising an osteoinductive composition.

64. The bone cement system of claim 52 wherein said the
particle size of said buffering compound is from about 5μ to 500μ .

65. The bone cement system of claim 63 wherein said
osteoinductive composition comprises hydroxyapatite.

- 36 -

66. The bone cement system of claim 52, which, upon mixing of the system parts, forms a bioerodible polymeric semi-IPN alloy having the mechanical properties set forth in Table 1.

5 67. A three part bioerodible bone cement system which upon mixing of the system parts forms a bioerodible polymeric semi-IPN alloy, consisting of

10 a) a first part comprising a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation; and a therapeutically effective amount of a biologically active or therapeutic agent; and

15 b) a second part comprising a second bioerodible scaffolding polymer which upon crosslinking provides a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy; and crosslinking agent for said second bioerodible scaffolding polymer; and

c) a third part comprising crosslinking initiator.

20 68. The bone cement system of claim 67 further comprising in one of said parts a buffering compound that buffers said acidic products within a desired pH range.

25 69. The bone cement system of claim 67 wherein said second bioerodible polymer comprises polypropylene fumarate (PPF).

70. The bone cement system of claim 67 wherein said crosslinking agent is a vinyl monomer.

30 71. The bone cement system of claim 70 wherein said crosslinking agent is vinyl pyrrolidone.

72. The bone cement system of claim 71 wherein said crosslinking agent is methyl methacrylate (MMA).

- 37 -

73. The bone cement system of claim 67 further comprising in one of said parts a biologically active or therapeutic agent.

5 74. The bone cement system of claim 73 wherein said biologically active or therapeutic agent is selected from the group consisting of bone repair proteins, antibiotics, cells, and mixtures thereof.

10 75. The bone cement system of claim 67 wherein said first bioerodible polymer is different from said second bioerodible polymer.

15 76. The bone cement system of claim 67 wherein said first bioerodible polymer is selected from the group consisting of poly(lactide-co-glycolide) (PLGA); polydioxanone; poly(ϵ -caprolactone); polyanhydrides; poly(ortho esters); copoly(ether-esters); polyamides; polylactones; polypropylene fumarates ($\text{H}[-\text{O}-\text{CH}(\text{CH}_3)-\text{CH}_2-\text{O}-\text{CO}-\text{CH}=\text{CH}-\text{CO}-]_n\text{OH}$); and combinations thereof.

20 77. The bone cement system of claim 68 wherein said buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of inorganic acid salts; organic acid salts; and polymeric organic acid salts.

25 78. The bone cement system of claim 68 wherein said buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of citric acid and sodium bicarbonate; calcium carbonate; calcium phosphate; calcium acetate; calcium citrate; calcium succinate; hydrolyzable polyamines; poly(N-vinyl carbazole); poly(acrylic acid); poly(acrylamide); and mixtures thereof.

35

- 38 -

79. The bone cement system of claim 68 wherein said buffering compound that buffers said acidic products within a desired pH range is selected from the group consisting of citric acid and sodium bicarbonate; calcium carbonate, calcium phosphate, calcium acetate, calcium citrate, calcium succinate, and mixtures thereof; said alloy further comprising an osteoinductive composition.

80. The bone cement system of claim 68 wherein said the particle size of said buffering compound is from about 5μ to 500μ .

81. The bone cement system of claim 79 wherein said osteoinductive composition comprises hydroxyapatite.

82. The bone cement system of claim 67, which, upon mixing of the system parts, forms a bioerodible polymeric semi-IPN alloy having the mechanical properties set forth in Table 1.

83. A method of bone repair comprising the steps of

- a) applying a bioerodible polymeric semi-IPN alloy to bone, said alloy comprising a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation; a second bioerodible scaffolding polymer which provides a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy; and a particulate soluble buffering material which dissolves *in vivo*; and
- b) allowing pores suitable for bone cell ingress to develop in said alloy by allowing said soluble filler to dissolve.

84. The method of claim 83 wherein said alloy further comprises an osteoinductive material.

- 39 -

85. A bioerodible polymeric semi-IPN alloy comprising
- a) from 3-50% by weight, based on the total weight of said alloy, of a first bioerodible polymer capable of producing acidic products upon hydrolytic degradation;
 - b) from 30-50% by weight of a second bioerodible scaffolding polymer which upon crosslinking provides a biopolymeric scaffolding or internal reinforcement for said semi-IPN alloy; and
 - c) from 1-50% of an active or therapeutically beneficial additive in admixture with said first bioerodible polymer.

1/2





FIG. 1A



FIG. 1B

2/2

**FIG. 2****FIG. 3**

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US98/07569

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : Please See Extra Sheet.

US CL : Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 523/113, 114; 524/414; 525/411, 425, 439, 445, 903; 424/426; 623/16

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P ---- Y,P	US 5,644,049 A (GIUSTI et al.) 01 July 1997, abstract, column 2, lines 15-65, column 3, lines 20-35, column 12, line 40 to column 13, line 4, column 35, lines 27-43, column 40, lines 25-65, and column 41, lines 29-45.	1-3, 8-11, 17-20, 23-25, 85 ----- 1-3, 8-11, 17-20, 23-25, 85



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Z" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

24 JUNE 1998

Date of mailing of the international search report

30 JUL 1998

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

ANDREW E.C. MERRIAM

Telephone No. (703) 308-2351

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US98/07569

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P ---- Y,P	US 5,645,592 A (NICOLAIS et al.) 08 July 1997, abstract, column 3, lines 10-25 and 58-68, column 4, lines 1-4, column 5, lines 1-45, column 6, line 52 to column 7, line 18, and column 9, line 65 to column 10, line 12.	1, 3, 8-10, 17-18, 20, 23-25, 51-52, 57-59, 67, 73, 75, 82, 85 ----- 1, 3, 8-10, 17-18, 23-25, 51-52, 57-59, 67-73, 75, 82-83, 85
Y	US 4,722,948 A (SANDERSON) 02 February 1988, abstract, column 2, line 65 to column 3, line 30, column 4, line 59 to column 5, line 12, column 5, line 40 to column 6, line 11 and column 11, line 42 to column 12, line 9.	1, 4-9, 12-18, 21-23, 25-26, 30-32, 35-36, 40-42, 51-59, 61-75, 77-85
Y,P	US 5,681,873 A (NORTON et al.) 28 October 1997, abstract, column 3, lines 38-68, column 4, lines 40-63, column 5, lines 27-44, column 7, lines 4-20, column 8, line 66 to column 9, line 12, column 9, line 55 to column 10, line 14, column 10, line 38 to column 11, line 14 and claims 1 and 12.	1-2, 12-16, 19, 52, 61-65, 68, 77-81, 83, 85

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US98/07569**Box I Observations where certain claims were found unsearchable (Continuation of Item 1 of first sheet)**

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of Item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Please See Extra Sheet.

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

☐

The additional search fees were accompanied by the applicant's protest.

☒

No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US98/07569

A. CLASSIFICATION OF SUBJECT MATTER:

IPC (6):

A61F 2/00, 2/28; A61K 33/42; C08G 81/00, 85/00; C08J 3/28; C08K 3/32

A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

523/113, 114; 524/414; 525/411, 425, 439, 445, 903; 424/426; 623/16

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

This application contains the following inventions or groups of inventions which are not so linked as to form a single inventive concept under PCT Rule 13.1. In order for all inventions to be searched, the appropriate additional search fees must be paid.

Group I, claim(s) 51-84 a semi-IPN (interpenetrated network) bone cement composition and product and method of making and using.

Group II, claim(s) 1-17 and 85, drawn to a semi-IPN polymer composition.

Group III, claims 18-25, drawn to an internal fixation device (IFD).

Group IV, claim(s) 26-47 drawn to a co-solvent method for making a semi-IPN.

Group V, claims 48-50, drawn to a melt mixing method of making a polymer semi-IPN.

The inventions listed as Groups I-V do not relate to a single inventive concept under PCT Rule 13.1 because, under PCT Rule 13.2, they lack the same or corresponding special technical features for the following reasons: Each of the semi-IPN compositions of groups I-V do not define a contribution which each considered as a whole makes over the prior art.

Elena Yakubsfeld

From: Kimberly A. Wattner
Sent: Thursday, February 24, 2011 3:18 PM
To: ssimmons@franksintl.com; 'Mike Webre'; Fletcher.Wheeler@franks.co.uk; jwheeler@franksfame.com; Guy Hustinx
Cc: Lee Huddleston; Brett A. Heller; Raejean Dorsey; Elena Yakubsfeld
Subject: Your Ref.: FP.09.11; Our Ref.: 17456/031002; Invoice; Reporting IDS Filed [No Action Required]
Attachments: 17456_031002Report of IDS filed and invoice attached.pdf; 17456_031002 Debit Note and New Matter Approval Form.pdf

Scott,

Please find the attached correspondence for your review and records.

Thank you,

Kim Wattner | Intellectual Property Assistant | **Osha Liang LLP** | 713.228.8600
Houston • Paris • Silicon Valley • Tokyo • Austin | www.oshaliang.com
This communication may contain confidential or privileged

2/24/2011